

Guide chemical resistance

✓ Resistant

Chemicals	Concentration	Multifix USF Tropical	Multifix US, USF Winter	Multifix Hybrid HSF	Multifix SE500	Multifix SE1000
Acetic acid	10%		✓	✓		
Acetone	5%			✓		
Ammonia, aqueous solution	5%	✓	✓		✓	✓
Ammonia, aqueous solution	32%					
Aniline	100%		✓			
Battery acid		✓	✓			
Boric Acid, aqueous solution		✓	✓		✓	✓
Calcium carbonate, suspended in water	All	✓	✓		✓	✓
Calcium chloride, suspended in water		✓	✓	✓	✓	✓
Calcium hydroxide, suspended in water		✓	✓		✓	✓
Carbon tetrachloride	100%	✓	✓		✓	✓
Caustic soda solution	10%	✓	✓		✓	✓
Caustic soda solution	40%				✓	✓
Chlorine water, swimming pool	All	✓	✓	✓	✓	✓
Chlorinated lime (Calcium hypochlorite)	10%			✓		
Citric acid	10%			✓		
Citric acid	All	✓	✓		✓	✓
Demineralized water	All			✓		
Diesel oil	100%	✓	✓	✓	✓	✓
Formaldehyde, aqueous solution	20%				✓	✓
Formaldehyde, aqueous solution	30%	✓	✓		✓	✓
Formic acid	10%				✓	✓
Freon		✓	✓		✓	✓
Fuel Oil		✓	✓	✓	✓	✓
Gasoline (premium grade)	100%	✓	✓	✓	✓	✓
Glycol (Ethylene glycol)		✓	✓		✓	✓
Hydraulic fluid	Conc.	✓	✓	✓		
Hydrochloric acid (Muriatic Acid)	Conc.					
Lactic acid	10%			✓		
Lactic acid	All	✓	✓			
Linseed oil	100%	✓	✓	✓	✓	✓
Lubricating oil	100%	✓	✓	✓	✓	✓
Magnesium chloride, aqueous solution	All	✓	✓		✓	✓
Motor oil (SAE 20 W-50)	100%	✓	✓		✓	✓
Oleic acid	100%	✓	✓		✓	✓
Perchloroethylene	100%	✓	✓		✓	✓
Petroleum	100%	✓	✓		✓	✓
Benzyl alcohol	100%			✓		
Phosphoric acid	85%	✓	✓		✓	✓
Phosphoric acid	10%		✓	✓	✓	✓
Potash lye (Potassium hydroxide)	10%	✓	✓		✓	✓
Potash lye (Potassium hydroxide)	40%	✓			✓	✓
Potassium carbonate, aqueous solution	All	✓	✓		✓	✓
Potassium chlorite, aqueous solution	All	✓	✓		✓	✓
Potassium nitrate, aqueous solution	All	✓	✓		✓	✓
Sea water, salty	All	✓	✓	✓	✓	✓
Sodium carbonate	All	✓	✓	✓	✓	✓
Sodium chloride, aqueous solution	All	✓	✓		✓	✓
Sodium phosphate, aqueous solution	All	✓	✓		✓	✓
Sodium silicate	All	✓	✓		✓	✓
Sulfuric acid	10%	✓	✓	✓		
Tartaric acid	All	✓	✓		✓	✓
Tetrachloroethylene	100%	✓	✓		✓	✓
Turpentine	100%	✓	✓		✓	✓

Results shown in the table are applicable to brief periods of chemical contact with full cured adhesive (e.g. temporary contact with adhesive during a spill).